

BONANZA

| | | | |
|------------------------------|--|---------------|------------|
| Manufacturing process | Tufted | | ISO 2424 |
| Gauge | 5/32" Loop | | |
| Pilecomposition | 100% PP | | ISO 2424 |
| Primary backing | Woven PP | | ISO 2424 |
| Secondary backing | AB + Felt | | ISO 2424 |
| Width | 400 cm, 500 cm | ± 1% | EN 986 |
| Pile weight | approx. 360 gr/m ² | | ISO 8543 |
| Total weight | AB : approx. 1496 gr/m ² Felt : approx. 1498 gr/m ² | ± 15% | ISO 8543 |
| Pile height | approx. 3,5 mm | | ISO 1765 |
| Total height | AB : approx. 5,3 mm Felt : approx. 6,0 mm | + 15% / -10% | ISO 1765 |
| Number of knots | approx. 106.155 /m ² | + 10% / -7,5% | ISO 1763 |
| Fire classification | AB : Efl Felt : Efl | | EN 13501-1 |
| Light fastness | ≥ 5 | | 105-B02 |
| Wearability | ≥ 4 | | 105-X12 |
| Water fastness | ≥ 4 | | 105-E01 |
| Thermal resistance | 0,120 m ² K/W | | ISO 8302 |
| Sound insulation | 0,10 dB | | ISO 10140 |
| GUT Nr. | Felt : 95BAF8E6 | | |

Floorsymbols Felt



Certificates

