























TECHNICAL CHARACTERISTICS

wineo 800			Covering type according to EN ISO 10582: Heterogeneous resilient-flooring for glueless installation	wineo
	wineo 800 wood	wineo 800 wood XL	wineo 800 stone XL	
Format	1212 x 185 mm	1505 x 237 mm	914 x 480 mm	
Product thickness	5 mm	5 mm	5 mm	
Planks, tiles / m² per box	8 / 1.79 m ²	6 / 2.14 m ²	6 / 2.63 m ²	
Boxes / m² per pallet	64 / 114.75 m ²	56 / 119.84 m ²	44 / 115.72 m ²	
Guarantee	25 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de			
Classification				Product composition
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices		1 Surface sealing
	Utilization class 33 Heavy-duty use in the commercial sector EN ISO 10874	Department stores, lobby's, schools, open plan offices, corridors		2 Surface texture Various embossings
	Utilization class 42 Normal use in the light industrial sector EN ISO 10874	Storage rooms, workshops		3 Wear layer Thickness 0.55 mm
	Wear resistance corresponding to the binder content – EN ISO 10582	Type I		4 Decor Decor film
	Wear resistance EN 660-2	Group T		5 Base layer with glass fibre reinforced
	Reaction to fire EN 13501-1	B _{fl} - s1		6 Profile connection Connect Technology 
	Anti slip category DIN 51130	R 9		7 Backing
	Slip resistance EN 13893	$\mu \geq 0.30 - DS$		Insulation mat silentCOMFORT (separately available)
	Anti-static properties EN 1815	$\leq 2 \text{ kV}$		stone - real joint technology selected decors
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		Certifications
	Light fastness EN ISO 105-B02	≥ 6		 <p>windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf</p> <p>Elastischer Bodenbelag DOP: 0501002 EN 14041:2004</p> <p>Resilient Flooring to be used within a building.</p>  <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p>  <p>Schadstoffgeprüft Emissionsgeprüft</p> 
	Residual indentation EN ISO 24343-1	$\sim 0.07 \text{ mm}$		
	Castor chair test EN 425 / ISO 4918	Type W – no visible change		
	Thermal resistance EN 12667	$\sim 0.033 \text{ (m}^2\text{K)/W}$ $\sim 0.0254 \text{ (m}^2\text{K)/W}$ in combination with silentCOMFORT		
	Impact sound reduction EN ISO 16251-1	$\sim 7 \text{ dB}$ up to 14 dB in combination with silentCOMFORT		
	Dimension stability EN ISO 23999	$\sim 0.1 \%$		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.